

31 31 16

(12) UK Patent Application (19) GB (11) 2 295 268 (13) A

(43) Date of A Publication 22.05.1996

(21) Application No 9523608.9

(22) Date of Filing 17.11.1995

(30) Priority Data

(31) 06283904	(32) 18.11.1994	(33) JP
07238879	18.09.1995	
07295768	14.11.1995	

(51) INT CL⁶

H01J 27/02 37/317, H05H 1/24

(52) UK CL (Edition O)

H1D DHBX D10 D12B13Y D12B3 D12B47Y D12B6
D12B8 D12B9 D14B D17AY D44 D9A D9CY D9C1X
D9C1Y D9C2 D9Y
U1S S1635 S2061

(71) Applicant(s)

Kabushiki Kaisha Toshiba

(Incorporated in Japan)

72 Horikawa-cho Saiwai-ku, Kawasaki-shi,
Kanagawa-ken, Japan

(56) Documents Cited

GB 1033447 A	EP 0537123 A	EP 0291185 A
US 5282652 A	US 5198677 A	

(58) Field of Search

UK CL (Edition N) H1D DHBB DHBX
INT CL⁶ H01J, H05H
Online : WPI

(72) Inventor(s)

Atsushi Murakoshi
Kyoichi Suguro
Tatsuya Hatanaka

(74) Agent and/or Address for Service

Batchelor, Kirk & Co
2 Pear Tree Court, Farringdon Road, LONDON,
EC1R 0DS, United Kingdom

(54) Ion generation device for ion implantation

(57) In an ion generation device which includes a chamber (51) in which plasma is generated, a first opening (52) for introducing gas to be ionized by the plasma, and a second opening (53) for irradiating ions generated from the gas, the inner wall of the chamber (51) is, or is coated with, metal or metal compound (60) which is resistant to chemical etching by the ions and radicals. Suitable resistant materials are V, Nb, Ta, Cr, Ti, Zr, Hf, Ni, Pb and Pt. A barrier layer may be provided between the chamber wall and its coating. The surface of the coating may be nitrided.




FIG. 7

GB 2 295 268 A

1/7




FIG. 1




FIG. 2




FIG. 3







FIG. 4






FIG. 6A




FIG. 6B




FIG. 6C




FIG. 7



FIG. 8




FIG. 9

6/7




FIG. 10




FIG. 11




FIG. 12







FIG. 13



FIG. 14



"ION GENERATION DEVICE, ION IRRADIATION DEVICE,
AND METHOD OF MANUFACTURING A SEMICONDUCTOR DEVICE"

The present invention relates to an ion generation
device for generating ions from gas or vapor by plasma,
5 an ion irradiation device, and a method of manufacturing
a semiconductor device.

Ion implantation has recently been employed as a
method of forming a pn junction by adding impurities
such as boron (B) and phosphorus (P) to a semiconductor
10 substrate. The ion implantation makes it possible to
accurately control the concentration and depth of
impurities to be diffused into a target spot.

FIG. 1 is a block diagram illustrating the
constitution of a prior art ion irradiation device.
15 The constitution will now be described in brief.

In the prior art ion irradiation device, an ion
source chamber 1 generates ions. The ions are drawn by
drawing electrodes 2 and their mass is analyzed by a
separating electromagnet 3. Then the ions are
20 completely separated by slits 4 and accelerated by
accelerators 5 to the final energy. A beam of the ions
is converged on the face of a sample 12 by a quadrupole
lens and scanned by scanning electrodes 7 and 8 such
that it is uniformly distributed onto the entire face
25 of the sample 12. Deflection electrodes 9 are designed
to deflect the ion beam in order to eliminate uncharged
particles caused by collision with residual gas.

The ion source chamber 1 is the heart of the ion irradiation device (including an ion generation device). As the chamber 1, there are a Freeman type ion source chamber using thermoelectrodes, a Bernas type ion source chamber, and a microwave type ion source chamber using magnetrons.

FIG. 2 is a cross-sectional view of a Freeman type ion source chamber 23. According to this chamber, plasma is generated by emitting thermoelectrons from a bar-shaped filament 22, an electric field is generated in parallel to the filament 22 by an electromagnet 21, a rotating field is caused by filament current, and electrons are complicatedly moved in the chamber 23 by a reflector 25, thereby improving in efficiency in ionization. The ions generated by the chamber 23 pass through a slit and are guided in a direction perpendicular to the filament 22.

FIG. 3 is a cross-sectional view of a Bernas type arc chamber 31 containing molybdenum (Mo) as the main ingredient. The chamber 31 includes a tungsten (W) filament 37 and its opposing electrode 34. The chamber is supplied with BF_3 gas from a gas line 32 and emits thermoelectrons from the filament 37, with the result that the BF_3 gas is discharged and ionized.

FIG. 4 is a cross-sectional view of a microwave ion source chamber. In this chamber, plasma is generated in a discharge box 43 using a microwave

caused by a magnetron 41. Since the chamber has no filaments, its lifetime is not shortened even by the use of reactive gas or it is not contaminated with alkali metal. However, metal as well as ions is
5 extracted from the chamber and attracted to the surface of a drawing electrode 44; therefore, a desired voltage cannot be applied or the metal or ions may reach a sample to contaminate it.

To resolve the above problems, an ion source
10 chamber for applying carbon (C) onto the inner wall of the chamber containing molybdenum (Mo) has been manufactured experimentally. Gases such as BF_3 and PF_3 has been conventionally employed in the above conventional devices. These gases are ionized in the chamber
15 to be implanted into source and drain regions serving as samples. In a compound semiconductor device, too, silicon (Si) is ion-implanted and, in this case, SiF_4 is used as source gas.

Ion implantation of germanium (Ge) has recently
20 been studied in order to render a semiconductor substrate serving as a sample amorphous. In the Ge ion implantation, GeH_4 gas (germane gas) has been employed; however, it reacts upon oxygen drastically, which causes security problems. Thus, GeF_4 is nowadays used
25 as source gas.

If the above-described Freeman type chamber is used for a long time, the filament is increased in

resistanc and finally disconnected, with the result
that no ions can be generated. Moreover, the chamber
is not discharged because of conduction of the chamber
and filament to be insulated by a supporting insulation
5 member.

According to the foregoing Bernas type arc
chamber, the molybdenum (Mo) on the inner wall of the
chamber is etched by fluorine ions, radicals or the
like produced by ionization of BF_3 , and the molybdenum
10 (Mo) is etched and removed from the inner wall. The
removed molybdenum absorbs on the tungsten filament 37
and electrode 34 and grown by thermal reaction into an
alloy of W and Mo. In this case, the thermoelectrons
are prevented from being emitted from the alloy region
15 of the filament 37 and supplied only to that region
thereof on which no molybdenum (Mo) absorbs, with the
result that the filament 37 is locally used up and
finally disconnected.

The disconnection of a tungsten filament used for
20 about 20 hours will be explained referring to FIGS. 5A
to 5C. Of these figures, FIG. 5A shows an unused
tungsten filament, FIG. 5B does the surface of the
tungsten filament when it is used for three days, and
FIG. 5C is a graph showing the results of observation
25 and composition analysis of a disconnected region of
the filament. As shown in FIG. 5B, a foreign
substance is included in a region of the filament where

no disconnection occurs. It is turned out from the composition analysis that the foreign substance is an alloy of the tungsten (W) filament and molybdenum (Mo) absorbing thereon. In contrast, it is apparent from FIG. 6B that no foreign substance is present in a disconnected region of the filament and the filament is finely formed. In the region containing the foreign substance, the composition ratio of W to Mo is 26 wt% to 74 wt%, that is, the principal ingredient of the substance is molybdenum, while in the region containing no foreign substance, the composition ratio of W to Mo is 87 wt% to 13 wt%.

Furthermore, the microwave ion source chamber has the drawback wherein carbon (C) is removed from the surface of the chamber and absorbs on the filament or a sample is contaminated with the carbon.

In the prior art ion source chambers described above, a filament is disconnected or a supporting insulation member deteriorates in insulation properties to shorten the lifetime thereof, a semiconductor substrate is contaminated, and the like.

It is accordingly an object of the present invention to provide an ion generation device, an ion irradiation device, and a method of manufacturing a semiconductor device, which are capable of lengthening the lifetime thereof and preventing a sample from being contaminated.

The inventors of the present invention considered the foregoing drawbacks of the prior art and have come to the following conclusion.

5 In an etching device wherein the density of plasma is high only in the vicinity of a substrate to be processed, molybdenum is chemically etched. However, it has been believed that there are relatively fewer cases where molybdenum of the inner wall of a chamber is etched by reacting upon ion or radical in the
10 chamber, such as an ion generation device, in which the inner wall is exposed and the density of plasma is low. However, the inventors carried out the following experiment in order to find problems due to the chemical etching.

15 The surface of the filament used for thirty hours in an Nb-coated chamber of an ion generating device supplied with GeF gas is shown in FIG. 5A (left side) which has been already used for the explanation of the related art. It is apparent from this figure that no
20 substance is attached to the surface of the filament and thus no reaction occurs between tungsten (W) and niobium (Nb).

The graph of FIG. 5A (right side) shows the results of surface analysis by measuring energy
25 incident upon the filament and number of absorption waves. As is apparent from FIG. 5C, when the incident energy reacting upon the tungsten (W) of the filament

is 8.4 keV, there occurs absorption and, when the incident energy reacting upon the niobium (Nb) is 2.3 keV, there occurs no absorption. It is thus understood that there would occur no reaction on the surface of the filament.

This is the point to which the inventors of the present invention directed their attention. That is, the above problems are resolved by coating the inner wall of the chamber with Nb which has a lower melting point, in which a compound of the Nb and halogen has a lower pressure.

FIG. 6A is cross-sectional view of the filament of the conventional Freeman ion source whose chamber is constituted of molybdenum. This filament was used for about twenty hours in the chamber supplied with GeF_4 gas. It is seen from FIG. 6A that the molybdenum adsorbs on the surface of the filament and grows by thermal reaction. The growth of molybdenum is seen from particles 100 of the molybdenum shown in FIG. 6B and the relationship between the incident energy and absorption waves as shown in FIG. 6C.

The growth of molybdenum appears to be caused by the fact that the molybdenum is etched and removed from the inner wall by chemical reaction upon fluorine ions and radicals in the plasma, and adsorbs on the filament.

Furthermore, the inventors acquired the following

results from the above experiment.

It turned out that the removal of molybdenum (Mo) occurred in using a prior art chamber for introducing BF_3 gas to implant boron ions to a sample, though it did not do more heavily than that of GeF_4 . While the lifetime of a filament in a chamber introducing BF_3 gas was about three months, that of a filament in a chamber introducing GeF_4 gas was about three weeks.

It also turned out that since molybdenum was removed even when BF_3 gas was used, the lifetime of a chamber was shortened by adsorption of the removed molybdenum to the filament or supporting insulation member or a sample was contaminated with the removed molybdenum. These problems became more serious when GeF_4 gas is introduced.

The inventors understood that it was the property of GeF_4 itself that made the above problems more serious. One reason is as follows. Three fluorine (F) radicals or ions are generated from BF_3 , while four fluorine radicals or ions are done from GeF_4 . It is thought that such a larger number of F radicals or F ions reacts upon a large amount of molybdenum thereby to acceleratedly shorten the lifetime of a chamber. This theory seems applicable to SiF_4 .

Another reason is a difference in ionizing efficiency between GeF_4 and BF_3 . More specifically, the electron gativity of Ge is 1.8 and that of F is

4.0, and thus the difference therebetween is 2.2, while the electron gativity of B is 2.0 and thus the difference between B and F is 2.0. The wider the difference in electronegativity, the higher the ionizing efficiency; thus, molybdenum is easier to remove and fluorine radicals or ions are easier to generate in the chamber using GeF_4 gas. A large amount of halogen is therefore generated in the chamber. This theory can be applied to Si the electronegative of which is 1.8.

The same problems as above arise in using PF_3 gas, though they are not more serious than in using CeF_4 gas. However, it is evident from the experiment that the problems can be resolved if the foregoing material is selected for the inner wall of a chamber in view of chemical etching.

The surface of a filament in a chamber having a Nb-coated inner wall in the ion generation device which was used for thirty hours, and the results of surface analysis obtained by measuring energy incident upon the filament and absorption therein, are also shown in FIG. 5A.

By resolving the above-described problems, the removal of materials of the inner wall can be prevented and so can be the absorption thereof in the filament. Moreover, a defect in insulation due to attachment of the materials to a supporting insulation member, as can

be contamination of a sample outside the chamber.

A supporting insulation member 76 (see FIG. 15) is spaced away from a plasma generation area and thus hard to directly expose to plasma. It is thus possible to prevent the materials of a filament from being attached to the supporting insulation member even when the filament is used for a long time.

In contrast, if a supporting insulation member 26 shown in FIG. 2 is used for a long time while being exposed to plasma, metallic materials are separated from the inner wall of the chamber and filament 22 and attached onto the surface of the member 26, resulting in bad insulation.

In the conventional microwave ion source, too, the molybdenum inner wall of the chamber, which is exposed to plasma, is etched by ions or radicals by chemical reaction, and the molybdenum is separated from the inner wall. The molybdenum is then removed from the chamber along with the ions and absorbs on the surface of the drawing electrode 44. As a result, a desired voltage cannot be applied or a sample is contaminated with the molybdenum.

According to present invention, by resolving the above problems, the etching of metallic materials are suppressed by virtue of reaction on the ions or radicals. It is thus possible to prevent the separated metallic materials from being attached to the filament

and drawing electrode and also to prevent a sample from being contaminated with the metallic materials.

According to a first aspect of the present invention, there is provided an ion generation device
5 comprises a chamber in which plasma is generated; a first opening, provided in the chamber, for introducing gas to be ionized by the plasma; and a second opening for irradiating ions generated from the gas, wherein at least an inner wall of the chamber is made of metal
10 which is resistant to chemical etching by the ions and radicals.

It is desirable that the gas be a compound including halogen.

The ion generation device of the present invention
15 is very effective in using GeF_4 , SiF_4 , BF_3 , PF_3 , and AsF_3 as the gas. Among them, SiF_4 and GeF_4 produce remarkable effects.

The chamber is provided with a filament for generating plasma by emitting thermoelectrons. It is
20 desirable that at least a surface of the filament be made of at least one metal used in the wall of the channels.

It is desirable that a compound of the metal of the inner wall and halogen has a vapor pressure which
25 is lower than that of a compound of the filament and halogen.

It is desirable that the metal material have

a melting point which is higher than an inside temperature of the chamber.

Specifically, it is desirable that the metal material contain at least one of V, Nb, Ta, Cr, Ti, Zr, Hf and Pt as a principal ingredient, and it is more desirable to use at least one of Va-family elements of V, Nb and Ta as the principal ingredient.

Moreover, when the inner wall of the chamber is coated with the metal material, it is desirable to provide a barrier metal between the chamber and metal material to prevent the material of the chamber from being seeped from the surface of the metal. It is then desirable to form Ti/TiN as the barrier metal. Also it is desirable that the uppermost surface of the metal material be coated with nitride. The nitride can be obtained by nitriding the uppermost surface of the metal material.

When the chamber contains molybdenum and the gas includes fluorine, it is desirable that a compound of the metal material and fluorine have a vapor pressure which is lower than that of MoF_6 .

It is desirable that the inner wall of the chamber is coated with the metal which is resistant to chemical etching by the ions and radicals.

Furthermore, the ion generation device further comprises a supporting insulation member for supporting the filament. It is desirable that the supporting

insulation member is separated from a generation area of the plasma. A spacer is provided between the supporting insulation member and the filament. In this case, it is desirable that the supporting insulation member is separated from the generation area of the plasma by leaving a space between the spacer and at least one of the filament and the inner wall of the chamber.

It is desirable that at least a surface of the spacer be made of at least one metal used in the wall of the chamber.

It is desirable that the foregoing ion generation device be of a Freeman type or a Bernas type.

It is desirable to employ noble metal or transition metal, which is resistant to plasma containing fluorine, in an ion source for generating ions by electric arc discharge, especially an area to be exposed to the plasma. Thus, backward sputtering onto the filament and poor insulation of the supporting insulation member can be suppressed, with the result that the lifetime of the ion source can be lengthened and the ion implantation can stably be achieved.

According to a second aspect of the present invention, there is provided an ion irradiation device comprising an ion generation section including a chamber in which plasma is generated, a first opening, provided in the chamber, for introducing gas

from which ions are generated by the plasma, and a second opening for irradiating the ions, at least an inner wall of the chamber being made of metal which is resistant to chemical etching due to the ions and radicals; and a sample chamber provided outside the chamber and including a sample so as to irradiate the ions from the second opening.

According to a third aspect of the present invention, there is provided a method of manufacturing a semiconductor device comprising the steps of introducing gas into a first chamber; generating ions from the gas by plasma generated in the first chamber; emitting the ions from the first chamber; and irradiating the ions onto a sample provided in a second chamber, wherein at least an inner wall of the first chamber is made of metal which is resistant to chemical etching due to the ions and radicals.

This invention can be more fully understood from the following detailed description of preferred embodiments by way of non-limiting example only when taken in conjunction with the accompanying drawings in which:

FIG. 1 is a cross-sectional view showing the constitution of a prior art ion irradiation device;

FIG. 2 is a cross-sectional view showing the constitution of a prior art Freeman type ion source;

FIG. 3 is a cross-sectional view showing the constitution of a prior art Bernas type ion source ;

FIG. 4 is a cross-sectional view showing the

constitution of a prior art microwave ion source;

FIGS. 5A to 5C are views showing a filament observed and analyzed to explain the prior art ion sources;

5 FIGS. 6A to 6C are views showing a filament is observed and analyzed to explain the prior art ion sources;

FIG. 7 is a cross-sectional view showing the constitution of a Bernas type ion source (ion
10 generation device) according to a first embodiment of the present invention;

FIG. 8 is a cross-sectional view showing the wall structure of a commonly-used ion source;

FIG. 9 is a cross-sectional view of the first wall
15 structure of the ion source shown in FIG. 7;

FIG. 10 is a cross-sectional view of the second wall structure of the ion source shown in FIG. 7;

FIG. 11 is a cross-sectional view of the third wall structure of the ion source shown in FIG. 7;

20 FIG. 12 is a cross-sectional view of the fourth wall structure of the ion source shown in FIG. 7;

FIG. 13 is a cross-sectional view of the fifth wall structure of the ion source shown in FIG. 7;

FIG. 14 is a cross-sectional view of the sixth
25 wall structure of the ion source shown in FIG. 7;

FIG. 15 is a cross-sectional view showing the constitution of a Freeman type ion source (ion

generation device) according to a second embodiment of the present invention;

FIG. 16 is a cross-sectional view showing another constitution of a Freeman type ion source which is
5 different from that in FIG. 15; and

FIG. 17 is a cross-sectional view showing still another constitution of a Freeman type ion source which is different from that in FIG. 15.

Embodiments of the present invention will now be
10 described with reference to the accompanying drawings.

In order to eliminate the problems of etching and depositing molybdenum (Mo) in the prior art ion source, the surface of an ion source, which is exposed to plasma including halogen, has to be covered with Va-
15 family metal (V, Nb, Ta) or noble metal (Ni, Pt, Pb), or the wall of the ion source has to be constituted by one of these metals or an alloy containing one of them as the main ingredient. It is desirable to use the Va-family metal whose melting point is higher than that of
20 the noble metal when the inside temperature of the ion source is 900 °C or higher. The prior art problems can be resolved by the embodiments of the present invention.

(First Embodiment)

FIG. 7 illustrates an example of a Bernas type ion
25 source (ion generation device) according to the first embodiment of the present invention. A TiN film of 100 nm and a Ti film of 50 nm are formed by sputtering

on an arc chamber 51 whose principal ingredient is molybdenum (Mo) (the TiN film is formed on the Ti film), an niobium (Nb) film of 3 μ m is formed by sputtering using an argon (Ar) gas, and an NbN film 60
5 of 1 μ m is coated thereon by sputtering in the one-to-one ratio of Ar gas to N₂ gas. The arc chamber 51 includes a tungsten filament 57 and filament supporting members 55 constituted of molybdenum. The supporting members 55 are not exposed to plasma generated in the
10 arc chamber 51 because barrier walls 58 are provided. In this case, filament stands 56, 59 pass through the barrier walls 58. It is desirable that the barrier walls 58 is constituted of molybdenum and the surface thereof are coated to suppress chemical etching due to
15 halogen, as shown in FIG. 7 of this embodiment.

BF₃ gas is supplied to the arc chamber 51 through a gas line 52, and the tungsten filament 57 emits thermoelectrons, thereby discharging the BF₃ gas and ionizing them.

20 The wall structure of a commonly-used ion source is shown in FIG. 8, and the basic wall structures of the ion source of the present invention are illustrated in FIGS. 9 to 14. The wall of the ion source as shown in FIG. 8 is constituted of molybdenum 61. In
25 contrast, as shown in FIG. 9, a Va-group metal (V, Nb, Ta) film 62, which is chemically resistant to halogen, especially fluorine, is coated on the surface of

molybdenum 61 and therefor the molybdenum is not etched at all. To cover the film 62 with a metal nitride 63, as shown in FIG. 10, is effective in reducing in chemical etching speed.

5 If the inside temperature of the ion source rises to 1000°C or higher (specifically, to 1500°C or higher), there occurs a problem wherein the molybdenum 61 reacts upon the Va-family metal to be seeped from the surface of the film 62. To resolve this problem,
10 as shown in FIGS. 11 and 12, it is effective to provide a reaction preventing layer 64 in the interface between the molybdenum and Va-family metal, and a metal nitride such as TiN, TaN and NbN can be used therefor. Si, C or Ge can be included in the metal nitride to stabilize
15 the wall structure even at a high temperature.

 In order to enhance the adhesion between the molybdenum and metal nitride, a metal film, which is thinner than the metal nitride, can be formed in the interface, and Ti, Zr, Hf, V, Nb and Ta are effective
20 as the metal film.

 In the first embodiment of the present invention, as shown in FIG. 13, no molybdenum is used, but a metal material whose principal ingredient is a Va-family metal can be solely employed. To cover the surface of
25 the film 62 with a nitride 63, as shown in FIG. 14, is also effective in suppressing chemical etching due to halogen. In this case, the foregoing reaction

preventing layer is not needed.

According to the first embodiment described above,
no etching occurs in the arc chamber 51 due to ions
such as fluoride and radicals or no foreign substances
5 are attached to the tungsten filament 57. The filament
57 becomes fine in its entirety and is finally dis-
connected. The lifetime of the filament 57 is greatly
lengthened to about 20 days, whereas that of the prior
art filament is only three days.

10 Further, according to the first embodiment of the
present invention, it is possible to prevent molybdenum
cross-contamination when BF_2^+ ions are implanted. Th
mass number of bivalent ions of molybdenum ($98/2 = 49$)
is the same as that of the BF_2^+ ions. In the
15 conventional arc chamber the main ingredient of which
is molybdenum, there occurs contamination of 10 to
1000 ppm in the ion implantation. In the present
invention, however, no molybdenum is mixed into the
ions to be implanted; therefore, the electrical
20 characteristics of the device are not influenced by the
contamination, and the ion implantation can cleanly be
achieved.

(Second Embodiment)

FIG. 15 illustrates an example of a Freeman type
25 ion source (ion generation device) according to the
second embodiment of the present invention.

According to the second embodiment, a chamber 73

is constituted of Mo and whose inner wall exposed by plasma is coated with Nb. The chamber 73 is so formed that a width is 7 cm, a height is 4 cm, and a depth is 4 cm, for example. A filament 72 has about 2 mm
5 diameter and is constituted of W which is commonly-used. Two electromagnets 71 are provided near the both sides of the filament 72. Insulation supporting members 76 is provided for the purpose of effecting insulation between the filament 72 and the chamber 73
10 and thereby effectively generating plasma. Further, the ion source has an opening 77 for introducing gas on one side thereof and a slit 74 for irradiating ions on the other side thereof.

GeF₄ gas is supplied from the opening 77 the to
15 ion source, with the result that thermoelectrons are emitted from the filament 72. Next, GeF₄ gas is discharged and ionized in the chamber 73. Ge ions generated by ionization are guided to a direction making right angles to the bar-shaped filament 72
20 through the slit 74, thereby converged on the face of a sample (not shown) by an ion beam apparatus or the like.

According to this second embodiment, since Nb
which is chemically resistant to F ions and F radicals
25 is coated on the inner wall of the chamber 73 exposed to plasma, the F ions and F radicals never etch the inner wall.

Accordingly, it is not considered that the metal is removed from the inner wall and absorbs on the filament 72 or the supporting insulation members 76, and therefore the lowering in resistance of the filament 72, the defect in insulation between the filament 72 and the chamber 73, and the contamination of the semiconductor substrate can be eliminated.

Moreover, each reflector (spacer) 75 expands to a direction vertical to the filament 72 and to a direction along the inner wall of the chamber 73. The spacer 75 is made of Mo, W, or the like. More preferably, V, Nb, Ta, Cr, Ti, Zr, Hf, Pt, or the like may be used as the material of the spacer 75. The supporting insulation members 76 are attached to the chamber 73 from outside thereof. With this construction, narrow space "a" between the chamber 73 and the spacer 75 is hold, thereby preventing the supporting insulation member 76 from being exposed to the plasma.

Assume that a length of the spacer 75 expanding from a surface of the inner wall vertical to the supporting insulation member 76 to a direction vertical to the filament 72 is "x", and a distance between the expanding spacer 75 and an inner wall of the chamber 73 is "y". Then, it is desirable to construct the ion source so that a relation " $x/y > 1$ " is established.

With this construction, not only the supporting insulation members 76 are not directly exposed to the

plasma, but also F ions and F radicals move randomly in the chamber 73, which is caused by conflict with the inner wall and separation due to ionization. In this manner, invasion of F ions and F radicals to the supporting insulation members 76 is suppressed.

5 Therefore, it can be realized that absorption of the filament material onto the supporting insulation members 76 caused by removal of the filament 72 itself is suppressed.

10 In this second embodiment, "x" is set at a value between 3 mm and 4 mm and "y" is set at a value between 2 mm and 3 mm. The relation " $x/y > 1$ " should be established, as described above. With this condition, it is thought that electrical short may occurs by

15 absorption of the removed metal onto the portion around the narrow space "a"; however such a problem never arise because the ion source is constructed so that metal removal is suppressed.

With these effects, it is capable of lengthening the lifetime of the ion source and preventing a sample from being contaminated.

20

FIG. 16 is a cross-sectional view showing another constitution of a Freeman type ion source which is different from that in FIG. 15. As shown in FIG. 16, spacers 75 and a filament 72 are formed integrally as one component. With this construction, the constitution of the ion source is simplified, and therefore

25

troubles in mechanism does not occur. Further, this makes easy to manufacture the ion source and makes lower the cost for manufacturing thereof.

5 FIG. 17 is a cross-sectional view showing still another constitution of a Freeman type ion source which is different from that in FIG. 15. As shown in FIG. 17, Nb is coated not only on the inner wall of the chamber 73 but also on the spacers 75 and the filament 72.

10 There may be used at least one of the metals used in the case of the wall of the ion source, other than Nb. Further, the filament 72 may be constituted of at least one of the metals used in the case of the wall of the ion source. In the case where the same type of
15 metal is used for each of the inner wall, the spacers 75, and the filament 72, the manufacturing for the ion source may become easy and its cost may be lowered. It is possible to use different types of metals for each of the inner wall, the spacers 75, and the filament 72.

20 It should be noted that the present invention is applicable to the case where only one of the spacers 75 and the filament 72 is coated with Nb.

25 With this construction, it is capable of suppressing the removal of the spacers 75 and the filament 72 itself. Therefore, this makes more hard to cause the defect in insulation and the reliability of the ion source is enhanced.

In the present invention, for example, the gas or vapor to be ionized is not limited to BF_3 or GeF_4 , and the filament is not limited to tungsten.

5 The present invention is more effective when it is applied to a Freeman ion source or a Bernas ion source using a filament; however, it is not limited to an ion source using a filament but can be applied to all ionization type devices.

10 The present invention can be applied to an ion irradiation device as well as the ion source (ion generation device). Moreover, the film forming and etching processes can be executed using the ions generated by the method described above.

15 Further, the present invention can be applied to a semiconductor device and a method of manufacturing the same. For example, an impurity diffusion layer such as source and drain regions of a MOSFET can be formed by adding impurities such as boron (B) and phosphorus (P) to a semiconductor substrate, or a contact resistance
20 to a diffusion layer can be lowered by implanting Ge ions into a silicon substrate. In an n-type conductivity MOSFET formed on a SOI (Silicon On Insulator) substrate, a semiconductor layer with a small band gap can be formed on a source region to
25 easily suppress a degradation in transistor characteristics due to accumulation of holes at the end of the source region while preventing impurities from

being mixed thereinto.

As described in detail above, according to the present invention, since the inner wall of a chamber is coated with metal having a resistance to chemical etching due to ions or radicals, a stable ion-implanting operation can be performed for a long time.

If a barrier metal is provided between a chamber and metal coated on the inner wall of the chamber or a nitride of the coated metal is coated on the surface of the coated metal, a stable ion-implanting operation can be carried out for a longer time.

Semiconductors can be modified according to the invention by substituting in Figure 1 the ion generation device shown in dotted lines, with an ion generating device according to the invention. Ion implantation with improved purity of the target ion(s) can be carried out, and in apparatus wherein the ion producing filament (if that type is used) requires less frequent replacement.

CLAIMS

1. An ion generation device comprising:
a chamber in which plasma can be generated;
a first opening, provided in said chamber, for introducing gas to be ionized by the plasma; and
a second opening for irradiating ions generated from the gas,
wherein at least a surface of an inner wall of said chamber comprises metal or metal compound which metal or compound exhibits resistance to etching by ions and/or radicals.
2. A device according to claim 1, wherein in use said gas is a compound including halogen such as fluoride.
3. A device according to claim 2, wherein said gas is at least one of GeF_4 , SiF_4 , BF_3 , PF_3 , and AsF_3 .
4. A device according to any preceding claim, further comprising a filament, provided in said chamber, for generating the plasma by emitting thermoelectrons.
5. A device according to claim 4, wherein at least part of the surface of said filament also comprises metal or metal compound which exhibits resistance to etching by ions and/or radicals.
6. A device according to claim 4 or 5, further comprising a supporting insulation member for supporting said filament, said supporting insulation member being separated from an area of the chamber wherein the plasma is generated.
7. A device according to claim 6, wherein a

spacer is provided between said supporting insulation member and said filament, and said supporting insulation member is separated from the generation area of the plasma by leaving a space between said spacer and at least one of said filament and said inner wall of the chamber.

8. A device according to any one of claims 2 to 7, wherein a compound comprises metal and halogen and has a vapour pressure which is lower than that of a compound comprising element(s) of the filament and halogen.

9. A device according to any preceding claim, wherein said metal or compound has a melting point higher than an internal operating temperature of said chamber.

10. A device according to any preceding claim, wherein said metal or compound contains at least one of the following elements: V, Nb, Ta, Cr, Ti, Zr, Hf and Pt as a principal ingredient.

11. A device according to any preceding claim, wherein said chamber includes molybdenum and said gas includes fluorine.

12. A device according to claim 11, wherein a compound of said metal and fluorine has a vapour pressure which is lower than that of MoF_6 .

13. A device according to any preceding claim, wherein said inner wall of said chamber is coated with said metal or compound.

14. A device according to any one of claims 10 to 13, wherein said metal or compound contains at least one of the following elements: V, Nb and Ta as a principal ingredient.

15. A device according to any preceding claim, wherein a discrete barrier layer is provided between said chamber and said surface comprising metal or metal compound to reduce or prevent seepage of material of said chamber from a surface of said metal or metal compound.

16. A device according to any preceding claim, wherein the inner wall surface comprises a metal nitride coating.

17. A device according to any preceding claim, in the form of a Freeman ion generation device.

18. A device according to any one of claims 1 to 16 in the form of a Bernas ion generation device.

19. An ion irradiation apparatus including a device as claimed in any preceding claim and a sample chamber provided outside said chamber and including a sample so as to irradiate the ions from said second opening on to said sample.

20. A method of manufacturing or modifying a semiconductor comprising the steps of:
introducing gas into a first chamber;
generating ions from said gas by plasma generated in said first chamber;

emitting the ions from said first chamber; and
irradiating the ions onto a semiconductor provided in a second chamber,

wherein at least a surface of an inner wall of said first chamber comprises metal or metal compound which exhibits resistance to etching by ions and/or radicals.

21. A method of modifying a semiconductor which involves use of an apparatus as claimed in claim 19.

22. A semiconductor which has been modified by ion implantation by a method as defined in claim 21.

23. An ion generation device or ion irradiation apparatus substantially as herein described with reference to any one of Figures 7 to 17 of the accompanying drawings.

24. A method of modifying a semiconductor device by ion implantation substantially as herein described with reference to any one of Figures 7 to 17 of the accompanying drawings.

Relevant Technical Fields

(i) UK Cl (Ed.N) H1D (DHBB, DHBX)

(ii) Int Cl (Ed.6) H01J; H05H

Databases (see below)

(i) UK Patent Office collections of GB, EP, WO and US patent specifications.

(ii) ONLINE: WPI

Search Examiner
MR M J DIXON

Date of completion of Search
12 DECEMBER 1995

Documents considered relevant following a search in respect of Claims :-
ALL

Categories of documents

X:	Document indicating lack of novelty or of inventive step.	P:	Document published on or after the declared priority date but before the filing date of the present application.
Y:	Document indicating lack of inventive step if combined with one or more other documents of the same category.	E:	Patent document published on or after, but with priority date earlier than, the filing date of the present application.
A:	Document indicating technological background and/or state of the art.	&:	Member of the same patent family; corresponding document.

Category	Identity of document and relevant passages		Relevant to claim(s)
X	GB 1033447 A	(CSF) see chamber 1 with tantalum walls 2	1, 9, 10, 14
X	EP 0537123 A	(PROEL) see eg page 3, lines 34-38	1, 9, 13, 19-22
X	EP 0291185 A	(EATON) see molybdenum or tantalum walls 12	1, 4, 6, 9, 10, 14, 17, 19-22
X	US 5262652 A	(APPLIED MATERIALS) see especially column 5, line 61 to column 6, line 54	1-4, 6, 9, 11, 17-22
X	US 5198677 A	(USA) see liner 45 of tungsten or molybdenum	1, 4, 9

Databases: The UK Patent Office database comprises classified collections of GB, EP, WO and US patent specifications as outlined periodically in the Official Journal (Patents). The on-line databases considered for search are also listed periodically in the Official Journal (Patents).